

Research Article

# Application of Sandy Soil Development using Grouting: A New Approach

Vishal Arora\* and Manoj Kumar

G.B.N. Govt. Polytechnic Nilokheri, Karnal. Haryana, India

Accepted 26 Dec 2015, Available online 29 Dec 2015, Vol.5, No.6 (Dec 2015)

## Abstract

*The constructional activities in the coastal areas often demand deep foundations because of the poor engineering properties and the related problems arising from weak soil at shallow depths. The very low bearing capacity of the foundation bed causes shear failure and excessive settlements. Further, the high water table and limited depth of the top sandy layer in these areas restrict the depth of foundation thereby further reducing the safe bearing capacity. This paper discusses grouting as one of the possible solutions to the foundation problems of coastal areas by improving the properties of soil at shallow depths.*

**Keywords:** Grouting; sand; cement; shear strength; bearing capacity; settlement.

## 1. Introduction

The construction of structures on weak ground often requires the soil to be improved in order to ensure the safety and the stability of surrounding buildings. Ground improvement in granular soils can be achieved by different methods such as vibro-flotation, compaction piles, compaction with explosives, excavation and replacement, well point system, reinforced earth, grouting etc.

The selection of the most suitable method depends on a variety of factors, such as: soil conditions, required degree of the compaction, type of structures to be supported, maximum depth of compaction, as well as site specific considerations such as sensitivity of adjacent structures or installations, available time for completion of the project, competence of the contractor, availability of equipments and materials etc. Soil compaction can offer effective solutions for many foundation problems, and is especially useful for reducing total settlements in sands. However, efficient use of soil compaction methods requires that the geotechnical engineer understands all factors that influence the compaction process.

The poor quality soils, especially their low bearing capacity, make it necessary to improve their properties by stabilization. The compaction of soils is intrinsically dependent upon the vertical effective stress, the type and gradation of soil, etc. Broadly, a well-graded soil compacts more than a uniform soil and moisture content is a significant parameter.. Dynamic compaction can only be used to a maximum depth of

10m to 20m and will not yield good results when the water table is at shallow depths. A question has been raised as how to increase the relative density of loose sands located within shallow depths. It is an inevitable problem in dynamic soil improvement methods that vibration induced on the ground surface tends to loosen the cohesionless soils. Hence alternative methods for developing the density and strength of loose sand at shallow depths are required. Soil stabilization, with cement grouts injected under pressure, has come into widespread use in construction.

At present the method of grouting is highly prevalent in a number of branches of structural engineering; and in foundation engineering for the reinforcement of existing foundations beneath buildings and structures as well for strengthening the soils in their beds. The penetrability of soils, which can be characterized by the permeability and the dispersivity of the cement - water suspension, which can be characterized by its grain size distribution; serve as criteria for defining the possibility of the impregnation of a soil by cement grout. Moreover, the method is sufficiently economic, and does not require complex equipment, and is also ecologically safe for the environment.

Pressure grouting substantially alters the strength, modulus, failure strain, and mode of failure of sand. It would be both practical and useful to estimate the properties of the grouted sand from the constituent properties that will lead to proper selection of grouts. The compressive behavior of grouted sand will depend on the cohesive behavior of the grout, the groutsand

\*Corresponding author: Vishal Arora

adhesion (bonding), and the properties of the sand. The physical or chemical interaction, or both, of two materials at their interface is known as adhesion or bonding. The strength and type of this bond plays an important, though poorly understood, role in the mechanical behavior of chemically grouted geomaterials.

Cement grouting by impregnation in granular media is a widely used technique in civil engineering, applied in order to improve the mechanical characteristics of soils. The idea consists in incorporating a pressurized cement grout in the pore space of the soil. The setting of cement grout in the pore space increases both the strength and stiffness. Grouting is mainly responsible for the gain in cohesion by the material and only marginally affects the friction angle. The cohesion linearly varies with cement content, the magnitude of the cohesion gained by grouting and also the friction angle is a slightly increasing function of cement content. The increase in angle of friction is negligible with respect to cohesion.

The Mohr –Coulomb cohesion varies between 0.1 and 0.5 MPa depending on the cement content of the grout and the relative density of the soil and increases in proportion with the cement to water ratio. Introduction of a cementing agent into sand imparts two components of strength, one due to the cement itself and the other due to friction. The friction angle of cemented sand is similar to that of uncemented sands.

In the process of cement grouting, cement is used to fill the voids of soil mass and to render it impervious to percolating water and improve the strength and elastic properties of soil. The strength of soil increases with increase in cohesive strength and angle of internal friction arising from the bonding between soil grains and hydrated cements. Unconfined compressive strength of micro fine slag cement grouts increases with increase in curing time from 7 to 60 days and decreases in water cement ratio from 2 to 0.8. The weakly cemented sand shows a brittle failure mode at low confining pressures with a transition to ductile failure at higher confining pressures. The shear strength parameters - cohesion and angle of internal friction increase when grouted with cement. The water cement ratios have much influence in the control of strength gain of sandy soils. Admixtures are used in cement grouting as accelerator, retarder, antibleeder, fluidizer, expander, etc. These admixtures added to impart some additional properties, may affect the basic requirements such as viscosity and bleeding of cement grouts.

At lower cement/ water ratios, the increase in viscosity is not significant but viscosity considerably increases with higher cement/ water ratios. Significant contributions on the study of grout materials, properties, equipment and procedure for grouting has been made by several researchers. As grouting reduces pore size and alters pore structure of soil, the engineering properties such as strength, stiffness etc, are also influenced to a great extent. Even today the

grouting operations are based on thumb rules and existing practices rather than design principles and well defined procedures substantiated by research data. In this paper an attempt is made to study the improvement in the strength of grouted loose sand bed by cement grouting.

### Materials Used

River sand was used in the present study and was graded into fine (75  $\mu\text{m}$ - 425  $\mu\text{m}$ ), medium (425  $\mu\text{m}$ - 2 mm) and coarse (2mm- 4.75mm) fractions as per the ASTM and BIS classifications. The dry density of sand was kept at 14.5 kN/m<sup>3</sup>. The cement used for the study was 43 grade Ordinary Portland Cement, the properties of which are given in table 1. For improving the properties of cement grouts, certain additives are sometimes used. Various admixtures such as sodium silicate (accelerator), tartaric acid (retarder), and aluminium sulphate (antibleeder) were used in the present study. The additives used in the present study and its dosages are given in table 2.

### Experimental Set Up

The efficiency of the grouting process was also verified through load tests conducted on ungrouted/grouted sand beds. The initial tests for the assessment of improvement in load carrying capacity through densification, were conducted by filling the sand at the desired densities in small tanks of size 30cmx30cmx30cm. The density at loosest state was 13.1 kN/m<sup>3</sup> and at densest state, it was 16.2 kN/m<sup>3</sup>.

Improvement in shear strength of the soil can be obtained by improving both the  $c$  and  $\phi$  values. Grouting which alters the pore structure and enhances the bonding and interlocking between particles can give considerable improvement in  $c$  as well as  $\phi$  values. To place the grout within the pores of the granular medium, two methods were adopted. In the first method, the grout was deposited within the pores by hand mixing in order to get a uniform grouted bed. In the second, previously prepared sand beds were grouted with grouting material using a grout pump similar to the grouting operations in the field. In the first case, samples were obtained by thoroughly mixing soil and grouting material with hand.

Sand sample of medium size range was taken in a tray. The predetermined percentage of cement by weight of sand was added to the sand and thoroughly mixed using a trowel. 10% or 20% of water by the combined weight of sand and cement was added to the sand cement mixture to get a uniform mix so that the viscosity of the cement grout will be within the pumpable limits i.e., a Marsh funnel viscosity of 30-60 seconds. The mix was filled in the split mould of size 60mm x 60mm x 25mm (for conducting direct shear tests), in layers with uniform density, after hand impregnation of samples; it was kept under wet condition for 28 days for curing.

**Table 1** Cement Properties

S. no.	Property	Characteristic value
1	Std. Consistency	28%
2	Initial Setting time	131 minutes
3	Final Setting time	287 min.
4	Blaine's Surface	298500
5	Sp. gravity	3.14

**Table 2** Additives used in the present study

S. no.	Admixture	Chemical	Optimum dosage
1	Accelerator	Sodium Scilitate	0.5-3
2	Retarder	Tartaric Acid	0.1-0.5
3	Antibleeder	Aluminium Sulphate	Upto 20%

In second case, the grouting nozzle was kept in position (at lower level of tank) and sand bed was prepared in a tank of size 45cm x 45cm x 60cm at the loosest density of 13.1 kN/m<sup>3</sup>, density index Dr = 0% corresponding to initial void ratio (emax) of 0.98. The grouting setup consists of a grout chamber with agitator, air compressor, grouting nozzle and regulating valve. The grout was prepared at cement/water ratio of 0.1 and agitated well to get uniform grout solution which was poured into the grout chamber. In order to reduce the chances of segregation of the grout, an agitator was provided inside the grout chamber. Grout was pumped under a uniform pressure of 500 kPa into the prepared sand bed. The grouting nozzle was raised during the grouting operation at regular intervals in order to get uniform flow of grout over the entire thickness of sand bed. The grouted sample was kept under moist condition, for curing.

**Results and Discussions**

Earlier studies have indicated that the relative density of loose sandy soils can be substantially improved by different methods, and among these, vibration techniques are reported to be the most effective. The values of safe bearing capacity computed from the results of direct shear tests conducted on samples of medium sand compacted at different relative densities are given in table 3. It can be seen that the maximum safe bearing capacity achieved by maximum compaction in the laboratory is only 90.3 kN/m<sup>2</sup>, which may not be sufficient in case of foundations for multistoried buildings. Further, these method will be quite expensive in the field.


Hence, studies were initiated to see whether grouting with cement could be a simpler and economical alternative to this. Direct shear tests were conducted on medium sand samples (both untreated and treated with different percentages of cement) in a shear box of 60 x 60x 25mm, to determine the shear strength parameters. The variation in the shear strength with cement content (varying from 2 to 25% by weight of dry sand) at an initial water content

of 20% is shown increases with increase in cement content. The figure also shows the influence of the curing period of the specimens on the shear strength. Here also the results are as expected i.e. with increase in the curing period.


**Table 3** Characteristics of sand used

Sand	In Loosest State	At Natural State	In Densest State
Medium	13.1	34	90.3


The variations of stresses are shown in Fig. 2. Here also, as one would expect, the shear strength increases with increase in normal pressure. Fig. 3 shows the plot between shear stress and shear strain.



**Fig.1** Effect of cement content on shear strength of treated medium sand



**Fig.2** Effect of cement content on shear strength of treated medium sand



**Fig.3** Shear stress – Shear strain Curve

Fig. 4 shows the effect of initial water content of the grout on the shear strength for a cement content of 4%. It can be seen that the shear strength increases upto around 5 % of initial water content and thereafter a slight decrease in shear strength is seen and remains almost constant upto 25 % of initial water content.

It can be seen that the peak stress (at failure) goes on decreasing with increase in initial water content. Fig. 6 shows the stress – strain curves of grouted samples having different cement contents. It can be noticed that the stress-strain response exhibit a linear relationship prior to the peak, for all cement contents. Certain admixtures are used along with cement for improving the properties of grouts such as viscosity and stability.

But no study has been carried out on how this admixtures will affect the strength of the cement grout. Results of studies carried out in this direction are presented here. The effect of sodium silicate (used as accelerator) on shear strength of cement grouted medium sand having curing period of 7 & 28 days.




Fig.4 Effect of water content on shear strength of treated medium sand




Fig.5 stress – Shear strain Curve for treated medium sand for different cement contents

**Conclusion**

Based on the experimental investigations and test results, the following conclusions are made. The shear

strength of the loose sandy soil steadily increases with increase in cement content and also with curing period. The rate of increase in shear strength is very high at higher percentages of cement than at lower percentage. The stress strain response exhibit a linear relationship prior to the peak value for all cement contents and the peak stress decreases with increase in water content.

The value of cohesion intercept  $c$  and angle of shearing resistance  $\phi$  steadily increase with increase in cement content and also with curing period. The rate of increase in  $\phi$  value is only marginal beyond a certain value of cement content (approx. 15%). The effect of curing period is more significant at higher percentages of cement than at lower percentages. The effect of accelerator (sodium silicate) is to reduce the strength slightly, but while considering the other benefits such as improvement in properties like viscosity, stability and the early setting of the grout, this reduction in strength is within the tolerable limits. One has to be very careful in the use of tartaric acid (retarder) with cement grout. The results indicate a sharp decrease in shear strength value when the cement content is less than 0.15 %. The shear strength is found to increase with increases in percentage of aluminium sulphate (antibleeder), eventhough there is a slight reduction at lower percentage of this salt. Hence use of admixtures like sodium silicate, tartaric acid, and aluminium sulphate with cement do not adversely affect the strength of the grouted medium.

**References**

Bement.R.A.P and Selby.A.R;(1997), *compaction of granular soils by uniform vibration equivalent to vibrodriving of piles*, Geotechnical and geological engineering, 15,p 121-143.  
 Yilmaz.D, Babuccu.F, Batmaz.S, and Kavruk.F (2008), *Liquefaction analysis and soil improvement in beydag dam*, Geotech Geol Eng, 26: 211-224.  
 Ibragimov.M.N (2005), *Soil stabilization with cement grouts*, Soil mechanics and foundation engineering, Vol.No. 2, 67-72.  
 Ata.A, and Vipulanandan.C, (1998), *Cohesive and adhesive properties of silicate grout on grouted sand behavior*, J. Geotechnical and geoenvironmental engineering ASCE, Vol.124, No.1, p 38- 44  
 Maalej.Y, Dormieux.L, Canou.J, and Dupla.J.C; (2007), *Strength of a granular medium reinforced by cement grouting*, C.R. Mecanique ,335;87-92  
 Dano,C., Hicher,P.Y., and Taillez,S.(2004), *Engineering properties of grouted sands*, J.Geotechnical and Geoenvironmental engineering ,ASCE, Vol.130,No.3, 2004, p 328-338.  
 Clough,G.W., Sitar,N., Bachus,R.C.,and Rad,N.S (1981), *Cemented sands under static loading*, Journal of Geotechnical Engineering.Div., ASCE, Vol. 107,No. GT6, June 1981  
 Sinroja,J.M., Joshi,N.H., and Shroff,A.V.(2006), *Ground improvement technique using microfine slag cement grouts*, IGC 2006,14-16, Chennai, p 661- 664  
 Glory.J., Abraham,B.M., Jose,B.T., and Paul,B.(2001), *Improvement of bearing capacity of sandy soils by grouting*, The New Millennium Conference 14-16Dec,Indore(MP)  
 Jose, B. T., Lovely, K. M., Sridharan, A. and Abraham, B. M. (2000). *Effect of admixtures on the behavior of cement grouts*, Proc. Of the Indian Geotech. Con-2000. 229-232.  
 Littlejohn, G.S. (1982), *Design of cement based grouts*. Proc. Of Conf. on Grouting in Geotech. Engrg., New Orleans, Edited by Wallace Hayward Baker, ASCE, New York. 35- 48.