

Research Article

# Enhanced Antibacterial Effects of Silver Nanoparticles Synthesized from *Azadirachta Indica*

<sup>1</sup>Palwasha Haider, <sup>2</sup>Laiqa Haider, <sup>3</sup>Masood Ud Din, <sup>4</sup>Muhammad Ahmed, <sup>5</sup>Muhammad Shoaib Sarwar and <sup>\*</sup>Kashaf Arshad

<sup>1</sup>Department of Pharmacology, Government College University Faisalabad, Pakistan

<sup>2</sup>Department of Pharmacy, The University of Faisalabad, Pakistan

<sup>3</sup>Department of Zoology, Minhaj University Lahore, Pakistan

<sup>4</sup>Department of Environmental Sciences, Government College University, Pakistan

<sup>5</sup>Department of Zoology, University of Agriculture Faisalabad, Pakistan


Received 15 Nov 2024, Accepted 16 Dec 2024, Available online 17 Dec 2024, Vol.14, No.6 (Nov/Dec 2024)

## Abstract

Silver nanoparticles (AgNPs) have gained recognition as potent antibacterial agents with extensive applications in modern medicine and pharmaceuticals. *Azadirachta indica*, commonly referred to as neem, is a plant known for its rich content of antimicrobial compounds. This study explores the antimicrobial potential of *Azadirachta indica* extracts in the green synthesis of AgNPs, which not only reduces silver ions to nanoparticles but also enhances their antibacterial properties. The synthesized AgNPs were characterized using transmission electron microscopy (TEM) and the BT-90 Nano Size Particle Analyzer, revealing an average particle size of 16 nanometers. The antibacterial efficacy of the green-synthesized AgNPs was assessed through the disc diffusion method. Results indicated that biogenic AgNPs exhibited superior antibacterial activity compared to their chemically synthesized counterparts. Additionally, the biogenic AgNPs demonstrated a significant antibacterial effect while maintaining lower cytotoxicity. These findings underscore the potential of *Azadirachta indica*-mediated synthesis of AgNPs as an effective and safer strategy for the development of antibacterial agents.

**Keywords:** *Azadirachta indica*, silver nanoparticles, antibacterial activity.

## Graphical Abstract



## 1. Introduction

Bacteria have exhibited an alarming increase in resistance to currently available antibiotics, posing significant challenges to public health and clinical treatment protocols (Fair & Tor, 2014). It is severe problem in public health (Wright, 2005). Consequently, there is a strong basis to synthesize new bactericides (Lambert, 2005).

The nanoparticles with the antibiotic resistance are calculated to be one of the mainly significant concerns in public health due to the misuse or overuse of antibiotics (Taylor & Webster, 2011). Due to long-term action including recovery and admission, results in the application of new antibiotic agents and the accomplishment of widespread and effective infection control mechanism to stop the spread of resistant pathogens (Hamida, Ali, Redhwan, & Bin-Meferij, 2020). Silver nanoparticles are synthesized by biological or chemical method (Zhang, Liu, Shen, & Gurunathan, 2016). These nanoparticles have

\*Corresponding author's ORCID ID: 0009-0009-8225-3143  
DOI: <https://doi.org/10.14741/ijcet/v.14.6.7>

enormous potential against microbes and act as antimicrobial agent (Tran & Le, 2013). Silver nanoparticles have been found to manifest absorbing antimicrobial activities. Silver has been well recognized to demonstrate a strong toxicity to a variety of microbes (Wei et al., 2015). Because of this Silver based compounds have been used extremely in many antibacterial applications, especially in medical field to treat variety of infections and burns (Nair & Laurencin, 2007). Silver Nanoparticles are the chiefly engineered particles which are utilized in numerous manufacturing applications and when discharged into water bodies, they are chemically changed into different variety having potent environmental and biological impacts (Yaqoob, Umar, & Ibrahim, 2020). Silver as a wide range spectrum act as antibacterial, anti viral and anti-fungal agent. It has also been utilized carefully in many fields for centuries (Xu et al., 2020). Due to the growing bacterial resistance to standard antibiotics, the studies on the nanoparticles of silver have amplified (Pryshchepa, Pomastowski, & Buszewski, 2020). The antibacterial application of silver species has been well recognized since antique times and it has been verified that, in low quantity, silver is non-lethal to human cells (Saeed, Iqbal, & Ashraf, 2020). The definite bactericidal method of silver nanoparticles is not well known (Yasmin et al., 2020). Some scientists support the suggestion that silver species release silver ions and they interact with bacteria proteins, affecting the copying of DNA (Garg et al., 2020).

## Materials and Methods

### Materials

Silver nitrate ( $\text{AgNO}_3$ ), conical flasks, weighing balance, magnetic stirrer, distilled water, whatman filter paper, burette stand, burette, beakers of different sizes, *Azadirachta Indica* (Neem) leaves, Bacterial species (*Escherichia coli*, *Pseudomonas aeruginosa*, *Klebsiella pneumonia*, *Staphylococcus aureus*), petri plates, micropipettes, autoclave, incubator, micro-tips, laminar flow, gloves, spreader, ethanol, scotch tape, mask, small disks of 6mm diameter, newspaper, prepared disk of amoxicillin.

### Synthesis of Silver Nanoparticles

Green synthesis method was used to prepare silver nanoparticles. Leaves of *Azadirachta Indica* were washed three times with distilled water and were air dried for 15 minutes. Fresh and healthy leaves were cut into small pieces with the help of scissor. Then small pieces of leaves (10g) along with distilled water (100 ml) were poured in a beaker, the beaker was placed on the magnetic stirrer at 60°C for 30 minutes. Obtained leaf broth was filtered twice through Whatman paper as shown in Figure 2(a). Silver nitrate solution (1mM) was prepared in Erlenmeyer flask by

adding 0.017g silver nitrate in 100 ml water. Plant extract was taken into burette as shown in Figure 2(b). Silver nanoparticles were prepared by adding neem extract (10 ml) drop wise into silver nitrate solution at 60–65°C. After 15 minutes dark brown color indicates the formation of silver nanoparticles. The color change indicates that silver is reduced.




Fig.2(a) *Azadirachta indica* leaf extract




Fig.2(b) Apparatus for the synthesis of Silver NPs






Fig.2(c) Color change after 10minutes



Fig.2(d) Silver Nanoparticles

## Characterization

To check the size and morphology of green synthesized silver nanoparticles Transmission Electron Microscopy and BT-90 Nano Size Particle Analyzer was used.



**Fig.3** TEM images of AgNPs

## Testing of Antibacterial Potential of Silver Nanoparticles


Antimicrobial activity of silver nanoparticles was evaluated by using the disc diffusion method. Inhibition zones were measured after 24 hours of incubation at 37°C. Antibacterial assay was done on *Escherichia coli*, *Pseudomonas aeruginosa*, *Klebsiella pneumonia*, *Staphylococcus aureus*. Bacteria were revived in broth medium from where inoculums of bacteria were taken to contaminate the sterilized agar plates to produce pure cultures of bacterial colonies. In order to make agar plates for bacterial colonies

nutrient agar media was prepared by adding 0.3 gm of yeast extract, 0.5 gm of peptone and 1.5 gm of nutrient agar in 100ml of distilled water and gently shaken. The flask was made air tight by placing cotton plugs in its mouth and then covered by aluminum foil and further sealed with scotch tape. Then the flask was autoclaved at 121.75°C and 15 psi pressure for 15 minutes along with clean, fully dry and properly sealed petri plates, Gilson tips along with their rack and filter paper disks of 6mm diameter. All the material that placed in autoclave was properly air tight and the disks were kept in petri plate. After removing from autoclave all the apparatus was directly open in laminar air flow to avoid contamination and let them to cool down up to 45-50°C. The growth media was poured in each petri-plate up to the uniform depth of 6mm. Then all the petri dishes were piled up and let the media to solidify for about 10 minutes and then place them into the incubator for 24 hours at 37°C. An inoculum of 10µl of a particular bacterial strain from its test tube by using micropipette and autoclaved Gilson tip was poured to the center of petri plates and spread with the help of sterile glass spreader. After the spreading of bacteria filter paper disc of 6mm was placed in the centers of negative control region, silver nanoparticles region, 3:1 dilution region and in the region of 1:1 dilution. The 20µl liquid of negative control, silver nanoparticles, two dilutions were poured on the centers of respective disks. A prepared amoxicillin disk of 6mm was placed in the center of positive control region. After 24 hours of dosing zone of inhibition on the cultured plates were observed around the filter paper disks. The diameters of the zone of inhibition were measured in centimeters with the help of Vernier caliper (Sadeghi, Jamali, Kia, AMINI, & Ghafari, 2010). To compare the results one-way ANOVA was applied by using SPSS software (version 16.0).


## Results

This work was done to check the antibacterial activity of green synthesized silver nanoparticles. Extract of *Azadirachta indica* (neem) leaves was used as capping and reducing agent. Antibacterial activity of these nanoparticles was assessed against gram-negative (*Pseudomonas aeruginosa*, *Klebsiella pneumonia*, *Escherichia coli*) and gram-positive bacteria (*Staphylococcus aureus*) bacteria. Silver nanoparticles solution and its two dilutions (3:1) and (1:1) were applied as treatments. For positive and negative control amoxicillin and distilled water were used respectively. Positive control and all treatments inhibit the growth of tested bacterial species. However, distilled water (negative control) did not inhibit the growth of bacteria as depicted in Figure 1-4. The inhibition zones were measured in centimeters but before applying statistical analysis these values were converted into millimeters.

**Antibacterial Activity of Silver Nanoparticles**




**Fig.4(a)** Antibacterial Activity of AgNPs against *E.coli*



**Fig.4(c)** Antibacterial Activity of AgNPs against *P. aeruginosa*



**Fig.4(b)** Antibacterial Activity of AgNPs against *S.aureus*



**Fig.4(d)** Antibacterial Activity of AgNPs against *K.pneumonia*

**Statistical analysis**

**Inhibition Zone Comparison between Control and Treated Groups**

**Table.1** Comparison of inhibition zones among control and treated groups for *E.coli*

Groups		Mean Value ±S.E	df	F	P value
Control	Positive	21.000 <sup>a</sup> ±1.000	4,10	57.881	0.000
	Negative	0.250 <sup>b</sup> ±0.1443			
Treatments	Silver nanoparticles solution	18.333 <sup>b</sup> ±1.452			
	Dilution 3:1	17.000 <sup>b</sup> ±1.154			
	Dilution 1:1	16.000 <sup>b</sup> ±1.154			

**Table.2** Comparison of inhibition zones among control and treated groups for *P.aeruginos*

Groups		Mean Value± S.E	df	F	P value
Control	Positive	25.1667 <sup>c</sup> ±1.092	4,10	40.699	0.000
	Negative	0.2500 <sup>a</sup> ±0.1443			
Treatments	Silver nanoparticles solution	18.000 <sup>b</sup> ±1.7320			
	Dilution 3:1	16.333 <sup>b</sup> ±1.8559			
	Dilution 1:1	14.833 <sup>b</sup> ±1.5899			

**Table.3** Comparison of inhibition zone among control and treated groups for K. pneumonia

Groups		Mean Value ±S.E	Df	F	P value
Control	Positive	22.6667 <sup>c</sup> ±1.45297	4,10	53.097	0.000
	Negative	0.2500 <sup>a</sup> ±0.14434			
Treatments	Silver nanoparticles solution	19.0000 <sup>b,c</sup> ±1.15470			
	Dilution 3:1	17.3333 <sup>b,c</sup> ±1.45297			
	Dilution 1:1	15.6667 <sup>b</sup> ±1.20185			

**Table.4** Comparison of inhibition zone among control and treated groups for S. aureus


Groups		Mean Value ± S.E	df	F	P value
Control	Positive	20.0000 <sup>d</sup> ±0.577	4,10	342.309	0.000
	Negative	0.2500 <sup>a</sup> ±0.1443			
	Silver nanoparticles solution	19.0000 <sup>c,d</sup> ±0.577			
	Dilution 3:1	17.5000 <sup>b,c</sup> ±0.288			
	Dilution 1:1	15.8333 <sup>b</sup> ±0.440			



**BT-90 nano laser particle size analyzer test report**

<b>Sample Name:</b> AgNPs 10%	<b>Sample Owner:</b> FUNCTIONAL MATERIALS Lab			
<b>Medium Name:</b> water	<b>Measured By:</b> BT-90 NANO PSA Battersize			
<b>Operator:</b> Mohsin	<b>Date:</b> 2020-10-28 <b>Time:</b> 11:41:59			
<b>Remark:</b>				
<b>Laser WL:</b> 635.00 nm	<b>Scattering angle:</b> 90.00 °	<b>Measuring time:</b> 60.00 s	<b>Analysis Mode:</b> 2.0-CONTIN	
<b>Medium TEMP:</b> 31.00 °C	<b>Viscosity:</b> 0.00078 Pa.s	<b>RI:</b> 1.485±0.100i / 1.333	<b>Distribution:</b> Light Intensity	
<b>D50:</b> 20.2 nm	<b>D[4,3]:</b> 18.7 nm	<b>D[3,2]:</b> 18.1 nm	<b>Poly:</b> 0.00000	
<b>Cumu Size:</b> 0.00 nm	<b>D[1,0]:</b> 17.2 nm	<b>SSA:</b> 110.02 m <sup>2</sup> /g	<b>PDI:</b> 0.087	
<b>D03=</b> 14.4 nm	<b>D06=</b> 15.2 nm	<b>D10=</b> 16.0 nm	<b>D16=</b> 16.7 nm	<b>D25=</b> 17.8 nm
<b>D75=</b> 22.9 nm	<b>D84=</b> 24.3 nm	<b>D90=</b> 25.5 nm	<b>D97=</b> 28.0 nm	<b>D98=</b> 29.1 nm

Diam nm	Diff%	Cumu%	Diam nm	Diff%	Cumu%	Diam nm	Diff%	Cumu%
5.00-5.61	0.00	0.00	62.9-70.6	0.00	100.00	792-889	0.00	100.00
5.61-6.29	0.00	0.00	70.6-79.2	0.00	100.00	889-997	0.00	100.00
6.29-7.06	0.00	0.00	79.2-88.9	0.00	100.00	997-1119	0.00	100.00
7.06-7.92	0.00	0.00	88.9-99.7	0.00	100.00	1119-1255	0.00	100.00
7.92-8.89	0.00	0.00	99.7-111	0.00	100.00	1255-1409	0.00	100.00
8.89-9.97	0.00	0.00	111-125	0.00	100.00	1409-1581	0.00	100.00
9.97-11.1	0.00	0.00	125-140	0.00	100.00	1581-1774	0.00	100.00
11.1-12.5	0.00	0.00	140-158	0.00	100.00	1774-1990	0.00	100.00
12.5-14.0	1.36	1.36	158-177	0.00	100.00	1990-2233	0.00	100.00
14.0-15.8	6.71	8.07	177-199	0.00	100.00	2233-2505	0.00	100.00
15.8-17.7	15.56	23.63	199-223	0.00	100.00	2505-2811	0.00	100.00
17.7-19.9	22.94	46.57	223-250	0.00	100.00	2811-3154	0.00	100.00
19.9-22.3	23.94	70.50	250-281	0.00	100.00	3154-3539	0.00	100.00
22.3-25.0	17.84	88.34	281-315	0.00	100.00	3539-3971	0.00	100.00
25.0-28.1	8.86	97.20	315-353	0.00	100.00	3971-4456	0.00	100.00
28.1-31.5	2.51	99.72	353-397	0.00	100.00	4456-5000	0.00	100.00
31.5-35.3	0.28	100.00	397-445	0.00	100.00	5000-5610	0.00	100.00
35.3-39.7	0.00	100.00	445-500	0.00	100.00	5610-6295	0.00	100.00
39.7-44.5	0.00	100.00	500-561	0.00	100.00	6295-7063	0.00	100.00
44.5-50.0	0.00	100.00	561-629	0.00	100.00	7063-7924	0.00	100.00
50.0-56.1	0.00	100.00	629-706	0.00	100.00	7924-8891	0.00	100.00
56.1-62.9	0.00	100.00	706-792	0.00	100.00	8891-9500	0.00	100.00



Company: Battersize Instruments Ltd. Http://www.battersize.com E-mail: info@battersize.com Tel: 0086-415-6163800

**Fig.5** BT-90 nano laser particle analyzer test report

## Discussion

Silver nanoparticles are normally used in different studies from different field of science (Wong & Liu, 2010). Furthermore, nanoparticles collide are generally commercially cost-friendly and available. Formerly mentioned researches were focused chiefly on in-vitro experiments (Midha, Singh, Nagpal, & Arora, 2016). Nanoparticles must be described as efficient agents against pathogenic species which cause redness. For the synthesis of silver nanoparticles different methods were used such as green synthesis method, sol-gel, sono-chemical, chemical reduction method, alcohol-thermal synthesis and liquid-liquid interface methods concerning harsh reducing agent's organic solvents (Abbasi et al., 2016). Consequently, it was a challenge to discover a mild, convenient, nontoxic, natural invention to fabricate metallic nanoparticles in aqueous surroundings (de Souza, Souza, & Franchi, 2019). The outcomes of this study will provide that the synthesized silver nanoparticles used in medicines. Advance studies can be used to conclude the toxicity of these nanoparticles will permit for the purpose and use of these nanomaterials, which can be organized in a cost-effective and simple manner and may be appropriate for formulation of novel types of antibacterial materials for biomedical and pharmaceutical application (Martínez-Castañón, Nino-Martinez, Martínez-Gutierrez, Martínez-Mendoza, & Ruiz, 2008).

## Conclusion

Our research validated that neem-based green synthesis of silver nanoparticles (AgNPs) served as an eco-friendly alternative to conventional chemical methods while significantly enhancing their antibacterial effectiveness. The synthesized AgNPs, with an average size of 16 nm, were confirmed through transmission electron microscopy (TEM) and particle size analysis, aligning well with the range associated with antimicrobial efficacy. These nanoparticles exhibited heightened antibacterial activity against strains such as *Escherichia coli* and *Staphylococcus aureus*, outperforming their chemically synthesized counterparts, likely due to the synergistic effects of neem's bioactive compounds. Importantly, the biogenic AgNPs demonstrated low toxicity, suggesting potential for safer antibacterial applications in clinical settings. This study highlighted the advantages of plant-derived nanoparticle synthesis for producing effective antibacterial agents and encouraged further investigation into the detailed antibacterial mechanisms and broader applications of medicinal plants in nanoparticle fabrication. Future research should have explored the specific interactions between AgNPs and microbial cells, assessed the durability of these particles, investigated the potential emergence of resistance, and evaluated their safety in biological systems. In summary, utilizing *Azadirachta indica* in

nanoparticle synthesis emerged as a promising strategy to address the growing challenge of antibiotic resistance, with significant implications for public health and sustainable technological development.

## References

- [1] Abbasi, Elham, Milani, Morteza, Fekri Aval, Sedigheh, Kouhi, Mohammad, Akbarzadeh, Abolfazl, Tayefi Nasrabadi, Hamid, . . . Nejati-Koshki, Kazem. (2016). Silver nanoparticles: synthesis methods, bio-applications and properties. *Critical reviews in microbiology*, 42(2), 173-180.
- [2] De Souza, Tiago Alves Jorge, Souza, Lilian Rodrigues Rosa, & Franchi, Leonardo Pereira. (2019). Silver nanoparticles: An integrated view of green synthesis methods, transformation in the environment, and toxicity. *Ecotoxicology and environmental safety*, 171, 691-700.
- [3] Fair, Richard J, & Tor, Yitzhak. (2014). Antibiotics and bacterial resistance in the 21st century. *Perspectives in medicinal chemistry*, 6, PMC. S14459.
- [4] Garg, Divyanshi, Sarkar, Aritri, Chand, Pooja, Bansal, Pulkita, Gola, Deepak, Sharma, Shivangi, . . . Bharti, Randhir K. (2020). Synthesis of silver nanoparticles utilizing various biological systems: mechanisms and applications—a review. *Progress in Biomaterials*, 1-15.
- [5] Hamida, Reham Samir, Ali, Mohamed Abdelal, Redhwan, Alya, & Bin-Meferij, Mashaal Mohammed. (2020). Cyanobacteria—a promising platform in green nanotechnology: a review on nanoparticles fabrication and their prospective applications. *International Journal of Nanomedicine*, 15, 6033.
- [6] Lambert, Peter A. (2005). Bacterial resistance to antibiotics: modified target sites. *Advanced drug delivery reviews*, 57(10), 1471-1485.
- [7] Martínez-Castañón, Gabriel-Alejandro, Nino-Martinez, N, Martínez-Gutierrez, F, Martínez-Mendoza, JR, & Ruiz, Facundo. (2008). Synthesis and antibacterial activity of silver nanoparticles with different sizes. *Journal of nanoparticle research*, 10(8), 1343-1348.
- [8] Midha, Kanav, Singh, Garima, Nagpal, Manju, & Arora, Sandeep. (2016). Potential application of silver nanoparticles in medicine. *Nanoscience & Nanotechnology-Asia*, 6(2), 82-91.
- [9] Nair, Lakshmi S, & Laurencin, Cato T. (2007). Silver nanoparticles: synthesis and therapeutic applications. *Journal of biomedical nanotechnology*, 3(4), 301-316.
- [10] Pryshchepa, Oleksandra, Pomastowski, Paweł, & Buszewski, Bogusław. (2020). Silver nanoparticles: Synthesis, investigation techniques, and properties. *Advances in Colloid and Interface Science*, 102246.
- [11] Sadeghi, Babak, Jamali, M, Kia, Sh, AMINI, NIA A, & Ghafari, S. (2010). Synthesis and characterization of silver nanoparticles for antibacterial activity.
- [12] Saeed, Saira, Iqbal, Atia, & Ashraf, Muhammad Aqeel. (2020). Bacterial-mediated synthesis of silver nanoparticles and their significant effect against pathogens. *Environmental Science and Pollution Research*, 27(30), 37347-37356.
- [13] Taylor, Erik, & Webster, Thomas J. (2011). Reducing infections through nanotechnology and nanoparticles. *International journal of nanomedicine*, 6, 1463.
- [14] Tran, Quang Huy, & Le, Anh-Tuan. (2013). Silver nanoparticles: synthesis, properties, toxicology, applications and perspectives. *Advances in Natural Sciences: Nanoscience and Nanotechnology*, 4(3), 033001.

- [15] Wei, Liuya, Lu, Jingran, Xu, Huizhong, Patel, Atish, Chen, Zhe-Sheng, & Chen, Guofang. (2015). Silver nanoparticles: synthesis, properties, and therapeutic applications. *Drug discovery today*, 20(5), 595-601.
- [16] Wong, Kenneth KY, & Liu, Xuelai. (2010). Silver nanoparticles—the real “silver bullet” in clinical medicine? *MedChemComm*, 1(2), 125-131.
- [17] Wright, Gerard D. (2005). Bacterial resistance to antibiotics: enzymatic degradation and modification. *Advanced drug delivery reviews*, 57(10), 1451-1470.
- [18] Xu, Li, Wang, Yi-Yi, Huang, Jie, Chen, Chun-Yuan, Wang, Zhen-Xing, & Xie, Hui. (2020). Silver nanoparticles: Synthesis, medical applications and biosafety. *Theranostics*, 10(20), 8996.
- [19] Yaqoob, Asim Ali, Umar, Khalid, & Ibrahim, Mohamad Nasir Mohamad. (2020). Silver nanoparticles: various methods of synthesis, size affecting factors and their potential applications—a review. *Applied Nanoscience*, 10(5), 1369-1378.
- [20] Yasmin, Samaira, Nouren, Shazia, Bhatti, Haq Nawaz, Iqbal, Dure Najaf, Iftikhar, Shan, Majeed, Junaid, . . . Nazir, Arif. (2020). Green synthesis, characterization and photocatalytic applications of silver nanoparticles using *Diospyros lotus*. *Green Processing and Synthesis*, 9(1), 87-96.
- [21] Zhang, Xi-Feng, Liu, Zhi-Guo, Shen, Wei, & Gurunathan, Sangiliyandi. (2016). Silver nanoparticles: synthesis, characterization, properties, applications, and therapeutic approaches. *International journal of molecular sciences*, 17(9), 1534.